

EMC LABS, INC.

Laboratory Report
0162037

9830 S. 51st Street, Suite B109, Phoenix, AZ 85044
Phone: 800-362-3373 or 480-940-5294 - Fax: (480) 893-1726

Bulk Asbestos Analysis by Polarized Light Microscopy


NVLAP#101926-0

Client:	OCCUPATIONAL HEALTH TECH. INC.	Job# / P.O. #:	24856	146955
Address:	2220 E. BIJOU ST. STE 153	Date Received:	10/21/2015	
	COLORADO SPRINGS CO 80909	Date Analyzed:	10/22/2015	
Collected:	10/20/2015	Date Reported:	10/22/2015	
Project Name:	IRON MT.	EPA Method:	EPA 600/R-93/116	
Address:		Submitted By:	TOM ANTONSON	
		Collected By:		

Lab ID Client ID	Sample Location	Layer Name / Sample Description	Asbestos Detected	Asbestos Type (%)	Non-Asbestos Constituents
0162037-001 IMTS-10-20-15- ROCK		Sheetrock, Lt. Pink / Brown	No	None Detected	Cellulose Fiber 10% Fibrous Glass 2% Gypsum Quartz Carbonates 88%
0162037-002 IMTS-10-20-15- HIGH RD		LAYER 1 Cardboard, Brown	No	None Detected	Cellulose Fiber 98% Carbonates Gypsum Binder/Filler 2%
		LAYER 2 Coating, Tan	No	None Detected	Cellulose Fiber 3% Carbonates Gypsum Quartz Binder/Filler 97%



Analyst - Kurt Kettler



Signatory - Lab Manager - Ken Scheske

Distinctly stratified, easily separable layers of samples are analyzed as subsamples of the whole and are reported separately for each discernible layer. All analyses are derived from calibrated visual estimate and measured in area percent unless otherwise noted. This report applies to the standards or procedures identified and to the sample(s) tested. The test results are not necessarily indicative or representative of the qualities of the lot from which the sample was taken or of apparently identical or similar products, nor do they represent an ongoing quality assurance program unless so noted. These reports are for the exclusive use of the addressed client and that they will not be reproduced wholly or in part for advertising or other purposes over our signature or in connection with our name without special written permission. The report shall not be reproduced except in full, without written approval by our laboratory. The samples not destroyed in testing are retained a maximum of thirty days. The laboratory measurement of uncertainty for the test method is approximately less than 1% by area percent. Accredited by the National Institute of Standards and Technology, Voluntary Laboratory Accreditation Program for selected test method for asbestos. The accreditation or any reports generated by the laboratory in no way constitutes or implies product certification, approval, or endorsement by the National Institute of Standards and Technology. This report must not be used by the client to claim product certification, approval, or endorsement by NVLAP, NIST, or any agency of the Federal Government. Polarized Light Microscopy may not be consistently reliable in detecting asbestos in flux coverings and similar non-friable organically bound materials.

TO WHOM IT MAY CONCERN:

These analytical results are provided from a NIST certified laboratory. The sample location is not verified. The collection of these samples were not collected by a state certified Building Inspector and should be presented as additional information only. This sample will not meet requirements of the Colorado Department of Public Health & Environment. The information provided is for use by the client only and should not be interpreted by as having been collected by a state certified building collector.